

Linear Low Density Polyethylene FLEXUS 9212XP

Description:

Braskem FLEXUS 9212XP is a linear low density polyethylene (LLDPE) produced through metallocene catalyst which presents excellent impact and puncture strength, beyond a differential sealing performance comparing with another typical LLDPE. It contains a special package of slip additives which allow better CoF control after lamination.

Applications:

Films laminated for automatic packaging (FFS) of solids and liquids, co extrusion and general use.

Additive:

Slip package in high level
Blocking medium
Processing Aids Medium Level

Process:

Blow Film Extrusion

Control Properties:

	ASTM Method	Unit	Value
Melt Flow Rate (190/2.16)	D 1238	g/10 min	1.0
Density	D 792	g/cm ³	0.917

Properties:

Blown Film Properties^a

	ASTM Method	Unit	Value
Tensile Strength at Break (MD/TD)	D 882	MPa	35/25
Elongation at Break (MD/TD)	D 882	%	850/840
Tensile Modulus – 1% Secant (MD/TD)	D 882	MPa	150/160
Dart Drop Impact	D 1709	g/F50	700
Elmendorf Tear Strength (MD/TD)	D 1922	gF	230/790
Haze	D 1003	%	7
Gloss - Angle 60°	D 2457	-	84

(a) 40 µm thickness film, processed with 10% of LDPE in a 75mm screw diameter extruder with blow up ratio of 2.2:1. (MD: Machine Direction; TD: Transversal Direction).

Final Remarks:

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA – Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA.
2. These information reflect typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact our Application Engineering.
5. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25213-02-9
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.
7. Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will have internal contact with human body.
8. The content of this Data Sheet replaces previous revisions published for this product.
9. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition.