

Linear Low Density Polyethylene ML2400N

Description:

ML2400N is a linear low density polyethylene with narrow molecular weight distribution. It presents good flexibility and low warpage.

Process:

Injection Molding. Masterbatches.

Applications:

Injection of lids and closures, housewares, masterbatches and general purpose parts.

Resin Properties:

	ASTM Methods	Units	Values
Melt Flow Rate (190°C/2.16Kg)	D 1238	g/10 min	20
Density	D 1505	g/cm ³	0.926

Typical Properties:

Plaque Properties

	ASTM Methods	Units	Values
Tensile Strength at Yield ^a	D 638	MPa	12
Tensile Strength at Break ^a	D 638	MPa	11
Flexural Modulus – 1% Secant ^b	D 790	MPa	415
Shore D Hardness ^c	D 2240	-	49
Notched Izod Impact Strength @23°C ^b	D 256	J/m	NB
Vicat Softening Temperature @10N ^b	D 1525	°C	94
Deflection Temperature @0.455 MPa ^b	D 648	°C	46

NB = No Break. Test specimens obtained by compression mold according to ASTM D 4703. Plaque Thickness: a) 2mm. b) 3mm. c) 6mm

Final Remarks:

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA – Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
2. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact our Application Engineering.
5. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 25087-34-7.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.
7. Braskem does not recommend this grade for plastic containers of physiological saline and/or parenterally administered drugs.
8. The content of this Data Sheet replaces previous revisions published for this product.
9. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition.